

Golf Cart Seating (Trimming)

Construction Properties		Standard	Remarks
Thickness		1.20mm	+/- 0.10mm
Width		54"	-0.5" / +1"
Weight		26 oz/yd ²	+/- 3 oz/yd ²
Backing		Polyester	Knock Stitched
Roll Size		40 yards	Standard
Formulation(1)		CPSIA Compliance	6P < 1,000PPM
Formulation(2)		Proposition 65	Lead content < 90PPM
Physical Properties		Standard	Remarks
Tensile Strength	MD	≧67 lbf	3 cm
	CD	≧67 lbf	
Elongation	MD	≧100%	3 cm
	CD	≧100%	
Tear Strength	MD	≥13 lbf	Trapezoid
	CD	≧6 lbf	
Adhesion Strength	MD	≥3 lbf	3 cm
	CD	≧3 lbf	
Abrasion		3,000 cycles, wire screen	CFFA-1a
Flex Resistance		25,000 cycles	CFFA-10
Crocking Resistance		Dry - No Stain	CFFA-7
Blocking Resistance		Class 2	CFFA-4
Cold Crack Resistance		ASTM D1790 Impact at -25°C	Pass
Fire Resistance		FMVSS302	Pass
Anti-UV Resistance		UVA-340nm at 600 hours	Pass
Mildew Resistance		ASTM G-21	Pass