



Specification

Potable Water Liner With Scrim

Property	Specification	Tolerance	Test Method
Thickness	1.00mm (After embossing)	+/- 5%	Micrometer
Width	72"	-0, +1/2"	Off roll, relaxed
Fabric Weight	160 gram/m ²	Nominal	D751
Liner Weight	1280 gram/m ²	+/- 80 gram/m ²	D751
Tensile Strength	260 / 230 lbf/in	Minimum	D751
Elongation	15 / 20%	Minimum	D751
Tear Strength	50 / 35 lbf/in	Minimum	D751
Adhesion Strength	15 lbf/in	Average	D1876
Cold Crack Resistance	-27°C	Pass	D1790
Operating Temperature	0°F - 150°F -18°C - 66°C	---	---

Brochure disclaimer: All the test values are based on an average data in our lab and are believed to be true and accurate to the best of our knowledge.

This information does not constitute a warranty or guarantee, it will not relieve the user from the responsibility of the proper and safe use of the product.